

112.2 - Cemented Carbides (powder form)

SRMs 887-889 are prepared from sintered tungsten carbide base materials.

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	887	888	889
Description	Cemented Carbide (W-83,Co-10)	Cemented Carbide (W-64,Co-25,Ta-5)	Cemented Carbide (W-75,Co-9,Ta-5,Ti-4)
Unit of Issue	(100 g)	(100 g)	(100 g)
Carbon	(5.5)	(4.6)	(6.0)
Cobalt	10.35	24.7	9.50
Tantalum		4.77	4.60
Titanium			4.03

- Certified values are normal font
- Reference values are italicized
- Values in parentheses are for information only